



TIS™ 100-05 Series products are the high-efficiency insulation ones with thermal conduction properties.

The supplement of the insulation base film made by silica gel into the heat-conduction material creates a great effect on both the insulation and heat conduction.

Feature

- » High thermal conductive and High dielectric strength
- » Low thermal resistance with high voltage isolation
- » Resistant to tears and punctures

Application

- » Car Battery & Power Supply
- » Power semiconductors
- » Audio and Video components
- » Motor controllers

Typical Properties of TIS100-05 Series

Product Name	TIS109-05	TIS112-05	TIS118-05	Test Method
Color	Blue			Visual
Construction & Composition	Ceramic filled silicone elastomer / Fiberglass			*****
Thickness	0.23mm	0.3mm	0.45mm	ASTM D374
Specific Gravity	1.72g/cc			ASTM D297
Hardness	50 Shore 00			ASTM D751
Tensile Strength	425 Kpsi			ASTM D412
Continuous Use Temp	-45 °C to 180 °C			*****
Dielectric Breakdown Voltage	>3500 Vac			ASTM D149
Dielectric Constant	5.5 MHz			ASTM D150
Volume Resistivity	4.0X10 ³ Ohm-meter			ASTM D257
Flame Rating	94 V0			E331100
Thermal Conductivity	1.0 W			ASTM D5470

Standard Thicknesses:

0.009"(0.228mm) 0.012"(0.304mm) 0.018"(0.457mm)

Consult the factory alternate thickness.

Pressure Sensitive Adhesive:

Request adhesive on one side with "A1" suffix.

Request adhesive on double side with "A2" suffix.

Standard Sizes:

12" x 160'(304mm x 48.76M)

Individual die cut shapes can be supplied.

If you want to know our thermal Products, you can visit our website. . <http://www.ziitek.com>



Gap Fillers | Pouring sealant | Silicon tape | Thermally Conductive paste | Flake graphite | Thermally Conductive Insulators
Ceramic heat sinks | Thermally Conductive plastic | Thermally Conductive Adhesive Tapes

Canada: Tel: +001-604-2998559 E-mail: sales@thermazig.com	Taiwan: Tel: +886-2-22771007 Fax: +886-2-22771075 E-mail: raymond@ziitek.com.tw	Dongguan: Tel: +86-769-38801208 Fax: +86-769-83791290 E-mail: angus@ziitek.com	Kunshan: Tel: +86-512-57816297 Fax: +86-512-57816327 E-mail: kelvin@ziitek.com	Hangzhou: Tel: +86-0571-63850366 Fax: +86-0571-63850322 E-mail: alex@ziitek.com
--	---	--	--	---

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein.